

COATING WEIGHT CHART

HOT-DIP GALVANIZED (600)							
COATING CODE (English)	COATING CODE (Metric)	MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
G01		NO MIN	NO MIN	NO MIN	NO MIN	NO MIN	NO MIN
G20		0.17	0.34	31	61	0.10	0.20
G30	Z90	0.25	0.50	46	92	0.15	0.30
G40	Z120	0.34	0.67	61	122	0.20	0.40
G60	Z180	0.50	1.01	92	183	0.30	0.60
G90	Z275	0.76	1.51	138	275	0.45	0.90
G115	Z350	0.97	1.93	176	352	0.58	1.15
G140		1.18	2.35	214	428	0.70	1.40
G165		1.39	2.78	252	505	0.83	1.65
G185		1.56	3.11	283	566	0.93	1.85
G210		1.77	3.53	321	642	1.05	2.10

GALVANNEALED (625)							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
A01		NO MIN	NO MIN	NO MIN	NO MIN	NO MIN	NO MIN
A20		0.17	0.34	31	61	0.10	0.20
A25	ZF75	0.21	0.42	38	76	0.13	0.25
45A/45A		0.25	0.50	46	92	0.15	0.30
A40	ZF120	0.34	0.67	61	122	0.20	0.40
A50		0.42	0.84	76	153	0.25	0.50
A60	ZF180	0.50	1.01	92	183	0.30	0.60

ELECTRO GALVANIZED (525)							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
01G/01G		NO MIN	NO MIN	NO MIN	NO MIN	NO MIN	NO MIN
20G/20G		0.11	0.22	20	40	0.07	0.14
30G/30G		0.17	0.33	30	60	0.10	0.20
40G/40G		0.22	0.44	40	80	0.13	0.26
50G/50G		0.28	0.55	50	100	0.16	0.32
60G/60G		0.33	0.66	60	120	0.20	0.40
70G/70G		0.39	0.77	70	140	0.23	0.46
90G/90G		0.44	0.88	80	160	0.29	0.58
98G/98G		0.50	0.99	90	180	0.32	0.64

EG ONE-SIDE (550)							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
01G/00X		NO MIN	N/A	NO MIN	N/A	NO MIN	N/A
30G/00X		0.17	N/A	30	N/A	0.10	N/A
60G/00X		0.33	N/A	60	N/A	0.20	N/A
70G/00X		0.39	N/A	70	N/A	0.23	N/A
98G/00X		0.54	N/A	98	N/A	0.32	N/A

ELECTRO ZINC-NICKEL (575)							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
01N/01N		NO MIN	NO MIN	NO MIN	NO MIN	NO MIN	NO MIN
10N/10N		0.06	0.11	10	20	0.04	0.07
20N/20N		0.11	0.22	20	40	0.07	0.14
30N/30N		0.17	0.33	30	60	0.10	0.20
40N/40N		0.22	0.44	40	80	0.13	0.26

ALUMINIZED - TYPE 1 & TYPE 2 (700)							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
T1		NO MIN	NO MIN	NO MIN	NO MIN	NO MIN	NO MIN
T1-13		0.25	0.50	20	40	0.07	0.13
T1-25		0.50	1.00	38	76	0.13	0.25
T1-40		0.80	1.60	61	122	0.20	0.40
T1-60		1.25	2.50	92	183	0.30	0.60
T2		NO MIN	NO MIN	NO MIN	NO MIN	NO MIN	NO MIN
T2-65		1.22	2.43	99	198	0.33	0.65
T2-100		1.87	3.74	153	305	0.50	1.00

GALVALUME							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
AZ 50	AZM150	0.42	0.84	76	153	0.25	0.50
AZ 55	AZM165	0.46	0.93	84	168	0.28	0.55
AZ 60	AZM180	0.50	1.01	92	183	0.30	0.60

GALFAN							
COATING CODE		MILS SIDE 1	MILS 2 SIDE	G / M2 SIDE 1	G / M2 2 SIDE	OZ / FT2 1 SIDE	OZ / FT2 2 SIDE
GF30	ZGF90	0.25	0.50	46	92	0.15	0.30
GF45	ZGF135	0.38	0.76	69	138	0.23	0.45
GF60	ZGF180	0.50	1.01	92	183	0.30	0.60
GF75	ZGF225	0.63	1.26	115	229	0.38	0.75
GF90	ZGF275	0.76	1.51	138	275	0.45	0.90